



ISO-17025 Accredited Testing Laboratory

PJLA ISO/IEC 17025:2005 Testing Accreditation# 59423


Beta Analytic Inc.  
4985 SW 74 Court  
Miami, Florida 33155 USA  
Tel: 305-667-5167  
Fax: 305-663-0964  
info@betalabservices.com  
www.betalabservices.com

## Report of Biobased Content Analysis using ASTM-D6866-12

**Submitter:** Ecomass Korea Co., Ltd.  
**Submitter Label:** bio Plastic EM-H12501  
**Laboratory Number:** Beta-352052  
**Material:** Biobased Material  
**Date Received:** June 28, 2013  
**Date Reported:** July 02, 2013

**Mean Biobased Result : 27 % \***

**Proportions Biobased vs. Fossil Based indicated by  
14C content**



\* ASTM-D6866 cites precision on The Mean Biobased Result as +/- 3% (absolute). This is the most conservative estimate of error in the measurement of complex biobased containing solids and liquids based on empirical results. Real precision for readily combustible and homogenous materials (e.g. gasoline) and especially samples received as CO<sub>2</sub> (e.g. flue gas or CEMS exhaust) can be as low as +/- 0.5-2%. The result only applies to the analyzed material. Fluctuations in carbon content within a batch of product, gasoline or flue gas must be determined separately (e.g. averaged measurements of multiple solids or liquids, and single measurement of the combination of gas aliquots collected over time). The accuracy of the result as it applies to the analyzed product, fuel, or flue gas relies upon all the carbon in the analyzed material originating from either recently respired atmospheric carbon dioxide (within the last decade) or fossil carbon (more than 50,000 years old). "Percent biobased" specifically relates % renewable (or fossil) carbon to total carbon, not to total mass or molecular weight. Mean Biobased estimates greater than 100% are assigned a value of 100% for simplification.